

Description

Enkamat[®] 7020 is a three-dimensional turf reinforcement mat (TRM) made of continuous monofilaments fused at their intersections. Ninety-five (95%) percent of the Enkamat is open and available for soil, mulch and root interaction with filaments, creating the most effective Root Reinforcement Mat (R²M) available. Enkamat is manufactured from nylon to eliminate the buoyancy factor associated with submerged conditions and provide permanent TRM protection in vegetated channels as well as on slopes.

Recommended Applications

- Permanent erosion control for Green (vegetated) channels with expected shear stresses ≤ 10 psf.
- Permanent erosion control for moderate to steep slopes (≤ 1.5H:1V).
- Support and enhance performance of Ecosystem plants.
- Substrate for hydraulically applied Bonded Fiber Matrix (BFM) and other mulches for erosion control applications where low water flow and low to moderate shear stresses are expected

Technical Data

Mechanical Properties	Test Method	Units	Typical Roll Value	
			MD	CD
Tensile Strength	ASTM D 5035 (modified)	kN/m (lbs/ft)	3.5 (240)	2.1 (145)
Thickness	ASTM D 5199	mm (in)	19 (0.75)	
Mass/Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	407 (12.0)	
UV Stability	ASTM D G53 / ASTM D 5035 (modified)	% strength retained	80	

Performance Properties	Test Method	Units	Typical Roll Value
Permissible Velocity			
Product Only	Flume test ¹	m/s (ft/s)	6.1 (20)
30 minute, vegetated	Flume test ¹	m/s (ft/s)	5.8 (19)
50 hour, vegetated	Flume test ¹	m/s (ft/s)	4.2 (14)
Permissible Shear Stress			
Product Only	Flume test ¹	kN/m ² (lbs/ft ²)	0.53 (11.2)
30 minute, vegetated	Flume test ¹	kN/m ² (lbs/ft ²)	0.48 (10.0)
50 hour, vegetated	Flume test ¹	kN/m ² (lbs/ft ²)	0.38 (8.0)

1. Flume test performed at independent laboratory—data and details available upon request.

Packaging Data

Physical Properties	Units	Nominal Value	
Roll Dimensions [width x length]	m (ft)	0.99 x 84.4 (3.25 x 277)	1.93 x 27.5 (6.33 x 90)
Roll Area	m ² (yd ²)	83.6 (100)	53 (63.3)
Estimated Roll Diameter	cm (in)	109 (43)	69 (27)
Estimated Roll Weight	kg (lb)	35 (77)	25 (54)

To the best of our knowledge, the information contained herein is accurate. However, Colbond Inc. cannot assume any liability whatsoever for the accuracy or completeness thereof. Final determination of the suitability of any information or material for the use contemplated, of its manner of use and whether the suggested use infringes any patents is the sole responsibility of the user. Colbond Inc. 2004©