



Mirafi[®] HP370

Mirafi[®] HP370 is composed of high-tenacity polypropylene yarns, which are woven into a network such that the yarns retain their relative position. Mirafi[®] HP370 is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D 4595	kN/m (lbs/ft)	47.277 (3240)	39.398 (2700)
Tensile Strength (at 2% strain)	ASTM D 4595	kN/m (lbs/ft)	7.88 (540)	7.88 (540)
Tensile Strength (at 5% strain)	ASTM D 4595	kN/m (lbs/ft)	19.786 (1356)	22.763 (1356)
Tensile Strength (at 10% strain)	ASTM D 4595	kN/m (lbs/ft)	35.02 (2400)	35.02 (2400)
Factory Seam Strength	ASTM D 4884	kN/m (lbs/ft)	24.6 (1688)	
Flow Rate	ASTM D 4491	l/min/m ² (gal/min/ft ²)	1629.6 (40)	
Permeability	ASTM D 4491	cm/sec	0.05	
Permittivity	ASTM D 4491	sec ⁻¹	0.52	
Apparent Opening Size (AOS)	ASTM D 4751	mm (U.S. Sieve)	0.60 (30)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

NOTE: To obtain Secant Modulus, divide tensile strength by the appropriate strain level (i.e. Secant Modulus at 5% = 1,356/0.05 = 27,120 lbs/ft)

Physical Properties	Test Method	Unit	Typical Value
Mass/Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	298.32 (8.8)
Roll Dimensions (width x length)	--	m (ft)	4.5 (15) x 91 (300)
Roll Area	--	m ² (yd ²)	418 (500)
Estimated Roll Weight	---	kg (lbs)	121 (266)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.